

苏州展格新材料有限公司
www.zgxcl.com 15950058877

Typical Product Properties

BISCO® HT-820 – Firm Cellular Silicone

HT-820 is a firm grade silicone foam that offers improved durability and sealing. It is used to seal and protect various outdoor communication, lighting, and electronic enclosures from small dust particles, wind driven rain, and fire. It offers a higher tear and tensile strength than our lighter grade foams. BISCO® Silicones are available in various thicknesses and manufactured in roll form to allow fabricators to easily convert the material to the proper dimensions.

Features and Benefits

- Excellent memory and low stress relaxation reduces maintenance costs associated with gasket failures due to compression set and softening.
- Resistance to ultraviolet light, ozone, extreme temperatures, and flame enables consistent performance in all environments.
- Compact cell structure provides improved sealing performance.
- Available through distribution sites throughout North America, Europe, and Asia.

Applications

- Environmental seals to protect against penetration of dust, moisture, air, or light within outdoor enclosures such as lighting fixtures, HVAC units, and electronic cabinets.
- Enclosures requiring a more durable, high closure force gasket.

Installation

- Available with a pressure-sensitive adhesive on one or two sides to allow easy application to a variety of surfaces.

BISCO® HT-820		
PROPERTY	TEST METHOD	TYPICAL VALUE
PHYSICAL		
Color		Gray
Thickness , mm (inches) Tolerance		0.8 – 6.4 (1/32 – 1/4) See Reverse
Standard Width , mm (inches)		914 (36)
Density , kg/m ³ (lb./ft ³)	ASTM D 1056	368 (23)
Compression Force Deflection , kPa (psi)	Force measured @ 25% Deflection ASTM D 1056	110.3 (16)
Compression Set , % max.	ASTM D 1056 Test D @ 70°C (158°F) ASTM D 1056 Test D @ 100°C (212°F)	< 1 < 5
Tensile Strength , kPa (psi)	ASTM D 412	345 (50)
Elongation , %	ASTM D 412	55
FLAMMABILITY & OUTGASSING		
Flame Resistance	UL 94	Listed V-0 and HF-1
Flame Spread Index (L_s)	ASTM E 162	< 25
Smoke Density (D_s)	ASTM E 662 Tested @ 4.0 minutes Tested @ 1.5 minutes	< 50 < 20
Toxic Gas Emissions Rating	SMP-800C	Pass

The information contained in this Data Sheet is intended to assist you in designing with Rogers' BISCO Silicone Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' BISCO Silicone Foams for each application. The Rogers logo, Helping power, protect, connect our world and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2006, 2007, 2009, 2017 Rogers Corporation, All rights reserved. Printed in U.S.A., 0117-PDF, Publication #180-071 Page 1 of 2

BISCO® HT-820 – Firm Cellular Silicone (continued)

PROPERTY	TEST METHOD	VALUE
Environmental Properties		
Water Absorption	Internal: 24 hrs @ room temp.	0.80 %
UV Resistance	SAE J - 1960	No Degradation
Ozone Effect Rating	ASTM D 1171	0 (No Cracks)
Corrosion Resistance	AMS - 3568	Pass
Electrical & Thermal Properties		
Dielectric Constant	ASTM D 150	1.50
Dielectric Strength	ASTM D 149, Volts/mil	93
Dry Arc Resistance	ASTM D 495, Seconds	96
Volume Resistivity, Ohm - cm	ASTM D 257	10 ¹⁴
Thermal Conductivity, w/m °K (BTU in/hr/ft ² /°F)	ASTM C 518	0.11 (0.75)
Temperature Resistance		
Low Temperature Flex at -55°C (-67°F)	ASTM D 1056	Pass
Recommended Use Temperature, °C (°F)	Internal	-55° to 200° (-67° to 392°)

Standard Thickness Tolerance

Standard Thickness			Tolerance (Inches)
Inches		mm	
1/32	0.031	0.80	± 0.015
1/16	0.063	1.60	± 0.020
3/32	0.094	2.39	± 0.020
1/8	0.125	3.18	± 0.025
3/16	0.188	4.76	± 0.025
1/4	0.250	6.35	± 0.030

Width Tolerance (Cellular)

Nominal Width (Inches)	Tolerance (w/o PSA)	Tolerance (with PSA)
0 < T ≤ 3	± 0.063	± 0.031
3 < T ≤ 8	± 0.094	± 0.031
8 < T ≤ 12	± 0.125	± 0.031
12 < T ≤ 18	± 0.188	± 0.031
18 < T ≤ 26	± 0.219	± 0.063
26 < T ≤ 36	± 0.250	± 0.063

Notes:

1. All metric conversions are approximate.
2. Additional technical information is available.
3. Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' BISCO Silicone Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' BISCO Silicone Foams for each application. The Rogers logo, Helping power, protect, connect our world and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2006, 2007, 2009, 2017 Rogers Corporation, All rights reserved. Printed in U.S.A., 0117-PDF, Publication #180-071 Page 2 of 2